

## Technical Data Sheet



Stabond Corporation  
1722 W. 139<sup>th</sup> Street  
Gardena, CA 90249



310/380-6168  
310/329-2729 Fax



stabondlab@yahoo.com

## DESCRIPTION

---

STABOND W 626 is a water based, synthetic rubber coating that is formulated to form a tough, water resistant barrier when allowed to dry. It is typically used to seal RV wall cutouts and works best when used in a two-coat application.

## PROPERTIES

---

TYPE:	SYNTHETIC RUBBER	DRY TIME:	20-60 MIN.
APPLICATION TEMP.:	70°F TO 100°F	CURE TIME:	5 DAYS FOR ULTIMATE CURE -
SHELF LIFE:	ONE YEAR	OPEN TIME:	NA
WT/GAL:	9.8 LBS	VISCOSITY:	10000 CPS @ 75°F
COLOR:	WHITE, BLACK, NATURAL	SOLIDS:	48%

## APPLICATION

---

STABOND W 626 may be applied by brush or roller. The material should be applied to the surface that the end user wishes to seal and allowed to dry thoroughly. Due to the difficulty in coating a continuous film with no pinpricks or voids, it is best to apply a second coat of W 626 over the initial application. This process can be facilitated by using two different colors so that it is obvious when the second coat has been applied).

## STORAGE

---

Store at 70°F to 80°F. The containers should be kept closed when not in use. **DO NOT FREEZE.**

## CAUTION

---

This compound is nonflammable. Vapors are harmful if inhaled. It may cause eye and skin irritation. Avoid contact with eyes, skin, and clothing. Thoroughly read the SDS before using this product

## IMPORTANT

---

Suggestions for the use of this product are based on tests believed to be reliable; however, the user should determine suitability for the intended use by his own evaluation. Because the use of the material is beyond our control, neither the seller nor the manufacturer shall be liable for any injury, loss, or damage, direct or consequential, arising out of the use or inability to use this product. Seller and manufacturer's sole obligation shall be replacement of material proved to be defective.